PAINTING SCHEDULE Produced by: Taubmans Paints (PPG PTY LTD)



Project: Huntlee Estate

NON PREMIUM FAÇADE SPECIFICATION

SURFACE PREPARATION:

All Brickwork must be high pressure water washed prior to the application of the Armawall Primer & Armawall Sand High Profile system. The surface should be clean, dry and free from all dirt, dust, grease, oil, excessive mortar or mortar slurry and any other surface contamination. Any holes or defects may require patching with Armawall Coarse Patch mixed with 20% grey cement powder prior to coating system application. Surface preparation is the responsibility of the Applicator, Builder, Renovator or Main Contractor. Armawall Surface Preparation Products are designed to perform at their optimum when used as part of an Armawall Texture Coating System.

EXTERIOR PAINTING SCHEDULE

Building elemer	nt: External	Precast Vera	ndahs & Soffits	
Substrate:	Code:	Coat:	Coat Description:	Colour:
		Manufac	turer: Taubmans	
		1st	Armawall Primer (Water Based)	
Bare Brickwork		2nd	Armawall Sand (Medium Black Texture Roller)	ТВС
		3rd	Armawall Sand (Medium Black Texture Roller)	

Armawall Sand High Profile

PAINTING SCHEDULE Produced by: Taubmans Paints (PPG PTY LTD)



Project: Huntlee Estate

PREMIUM FAÇADE SPECIFICATION

SURFACE PREPARATION:

All Brickwork must be high pressure water washed prior to the application of the Armawall Roll on Render & Armawall Sand High Profile system. The surface should be clean, dry and free from all dirt, dust, grease, oil, excessive mortar or mortar slurry and any other surface contamination. Any holes or defects may require patching with Armawall Coarse Patch mixed with 20% grey cement powder prior to coating system application. Surface preparation is the responsibility of the Applicator, Builder, Renovator or Main Contractor. Armawall Surface Preparation Products are designed to perform at their optimum when used as part of an Armawall Texture Coating System.

EXTERIOR PAINTING SCHEDULE

Substrate:	Code:	Coat:	Coat Description:	Colour:
Bare Brickwork		Manufac	ufacturer: Taubmans	
		1 st 2nd	Armawall Roll on Render (Coarse Texture Roller) Left Bold Armawall Roll on Render (Coarse Texture Roller) Flattened	ТВС
		3rd	Armawall Sand (Medium Black Texture Roller)	
		4th	Armawall Sand (Medium Black Texture Roller)	

Armawall Sand High Profile

Please read the below Additional Notes in conjunction with the above Specification.



Additional Notes:

- Specification is built on the basis that no release agent was used on the precast concrete. A water bead test is highly recommended prior to coating.
- All blow holes in the tilt up concrete panels are to be filled with Armawall Smooth Patch mixed with 10% grey cement powder prior to its application.
- Moisture content in the substrate must below 15% wood moisture equivalent prior to and during the application of the specified Armawall texture system.
- Armawall Sand may not fill all blow holes or imperfections on the substrate. All surface preparation is highly recommended.
- Surface preparation is the responsibility of the Applicator, Builder, Renovator or Main Contractor. Armawall Surface Preparation Products are designed to perform at their optimum when used as part of an Armawall Texture Coating System.
- For optimum performance of the Armawall Texture Coating System it is strongly recommended that the application is carried out by an applicator skilled in the Armawall systems and products.
- It is a requirement for the home owner, builder, architect or main contractor to fully investigate the suitability of the Armawall Texture Range for it's desired use and application.
- Please refer to the specific Armawall Product Data Sheets for further information.